

BIODEGRADABLE THERMOFORMING SHEET GENERAL PHYSICAL PROPERTY

| Item | | Unit | Value | Test method |
|--------------------------------------|----|--------------------|-------|---------------|
| Specific gravity | | — | 1.17 | |
| Tensile strength | MD | kf/cm ² | 121 | ASTM D-882-02 |
| | TD | | 114 | |
| Tensile elongation at rupture | MD | kf/cm ² | 470 | ASTM D882-02 |
| | TD | | 16.8 | |
| Elongation | MD | % | 310 | JIS K 7113 |
| | TD | | 650 | |
| Deflection temperature under load | | °C | 39 | JIS K 7191 |

- Above value is not a guaranteed one but a measured one.

THAI META-PLAS CO., LTD.

3 Ramkhamhaeng 164 Road Yaek 9, Sub District Min Buri, District
Min Buri, Bangkok 10510, Thailand

Tel: 66-2-917-6490 Fax: 66-2-917-6489 Mail: info@thaimetaplas.com